



RTV664

Description

RTV600 series is comprised of RTV662, RTV664, and RTV668. Each is a two part, addition (platinum) curing mold making product offering high durometer for applications requiring greater dimensional stability.

RTV662 offers the highest durometer (68 Shore A) in the series, as well as the longest worklife. It is ideally suited for embossing, release rolls, and large molds.

RTV664 is a high durometer (62 Shore A), long work life product. It offers excellent chemical and abrasion resistance and was designed for high production on manufacturing lines.

RTV668 is a high durometer (62 Shore A) product formulated for sulfur resistance. It is ideal for casting with masters made of pine, oak, and elm.

Key Features and Benefits

- Excellent dimensional stability
- High tear strength
- High durometers (62/68 Shore A)
- Virtually no shrinkage (room temperature cure)

Typical Physical Properties

Product Base	RTV662A	RTV664A	RTV668A
Color	beige	beige	beige
Viscosity, cps	150,500	153,000	151,000
Specific Gravity	1.28	1.28	1.28
Catalyst	RTV662B	RTV664B	RTV668B
Color	blue	blue	green
Viscosity, cps	5,000	6,000	3,800
Specific Gravity	1.05	1.05	1.05
Mix Ratio, wt:wt	10:1	10:1	10:1
Catalyzed Properties			
Viscosity, cps	120,000	120,000	120,000

Worklife, hours	4	2	2
Potlife, hours	5	3	2.5
Demold time, hours	24	18	24
Shore A, 36 hours	68	62	62
Tensile, psi	1015	933	1041
Elongation, %	235	245	240
Tear, ppi	136	122	100
Service Temperature, °C (°F)	-60/200	-60/200	-60/200
	(-75/392)	(-75/392)	(-75/392)
Linear Shrinkage, %	< 0.2	< 0.2	< 0.2

Potential Applications

- Architectural and furniture molding
- Prototyping

Processing Recommendations

Mixing

Select a mixing container 4-5 times larger than the volume of RTV silicone rubber compound to be used. Weigh out the RTV silicone rubber base compound and add the appropriate amount of curing agent. With clean tools, thoroughly mix the RTV base compound and the curing agent, scraping the sides and bottom of the container carefully to produce a homogenous mixture. When using power mixers, avoid excessive speeds which could entrap large amounts of air or cause overheating of the mixture, resulting in shorter pot life.

Deaeration

Air entrapped during mixing should be removed to eliminate voids in the cured product. Expose the mixed material to a vacuum of about 29 in. of mercury. The material will expand, crest, and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing ceases.

Automatic equipment designed to meter, mix, deaerate, and dispense two-component RTV silicone rubber compounds will add convenience to continuous or large volume operations.

Curing

RTV662, RTV664, and RTV668 silicone rubber compounds will cure sufficiently in 24 hours at 25C (77F). To achieve faster cure speeds, elevated temperatures may be used.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at www.momentive.com or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

From automotive to healthcare, from electronics to construction, products from Momentive Performance Materials Inc. are practically everywhere you look. We are a global leader in silicones and advanced materials with a 70+ year heritage of innovation and being first to market – with performance applications that improve everyday life. By knowing our customers' needs and creating custom technology platforms for them, we provide science based solutions to help customers increase performance, solve product development issues and engineer better manufacturing processes.

Contact Information

For product prices, availability, or order placement, contact our customer service by visiting www.momentive.com/Contacts

For literature and technical assistance, visit our website at: www.momentive.com

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.

DISCLAIMER

The information provided herein was believed by Momentive Performance Materials Inc. (collectively with its subsidiaries, "Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for user's intended application or use. All products supplied by Momentive are subject to Momentive's standard terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE**, except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any products.